

• TECHNICAL DATA TENCATE COTTON

Reference	Test method	KZ-99
Material		100% cotton
Finish		water- and dirtrepellent
Width	ISO 22198	160 cm
Weight (+/- 5%)	ISO 3801	135 g/m ²
Tensile strength	ISO 13934-1	
Warp (5 cm)		500 N
Weft (5 cm)		400 N
Tearing strength	ISO 13937-1	
Warp (4,3 cm)		10 N
Weft (4,3 cm)		10 N
Dimensional change in wet condition	NFG 07-052	
Warp		- 4 %
Weft		- 0,5 %
Colour-weather fastness	ISO 105 B04	≥4

Please note that if you combine materials, such as ground sheet, mud skirts, windows, zips, etc., these products may have an adverse effect on each other. This is your own responsibility and we therefore advise you to carry out extensive tests beforehand. *The watercolumn value is an average value. Individual measurements can deviate + and - 15% from this average. These deviations in individual parties have no(negative) influence on water-repellent or water-resistant properties of the tent textile.